



# Niax\* catalyst A-33

## Niax\* catalyst A-33

### Description

Niax catalyst A-33 imparts a high level of activity and good physical properties to flexible foam systems. Optimum performance of this catalyst can be achieved when it is used in conjunction with Niax catalyst E-A-1 or Niax catalyst A-10 in flexible foam formulations.

### Typical Physical Properties

Specific Gravity at 20°C (68°F)	1.033
Average Weight per Gallon, lb	8.59
Viscosity, cP	
at 0°F (-17.8°C)	7000
at 36°F (2.2°C)	700
at 75°F (23.9°C)	100
Solubility at 20°C (68°F)	
in Water	Infinite
in Urethane-Grade Polyol	Completely miscible
in Fluorocarbon Polyol	50% by wt
Vapor Pressure, mm Hg	
at 100°F (37.8°C)	2
at 200°F (93.3°C)	17
at 300°F (148.9°C)	65
Flash Point, Pensky-Martens Closed Cup <sup>(1)</sup> , °C (°F)	88 (190)
Storage Life	Unlimited in enclosed container

(1) ASTM D 93

### Processing Recommendations

Niax catalyst A-33 was evaluated using bench foam techniques. The effects of varying tin at constant amine and varying amine at constant tin were both evaluated. The ranges of tin and amine concentrations were well within the “operating range” of each. The dependent variables measured were: reactivity, top collapse, height of rise, breathability, density, cell count, and foam hardness (IFDs). Top and bottom gradients for breathability and density were defined.

Table 1 shows the foam screening formulation and foaming conditions. Table 2 provides evaluations of the foams produced at various tin and amine levels using Niax catalyst A-33 and a Niax catalyst A-10/Niax catalyst A-33 blend.

**Table 1: Test Foam Formulation and Foaming Conditions**

Foam Formulation	Parts by Wt
3000 MW EO/PO Polyol	100.0
CFC-11 Blowing Agent	5.0

Niax\* catalyst A-33

Methylene Chloride	3.0
Water	4.5
Amine Catalyst	Varied
Niax Silicone L-580	1.5
Stannous Octoate, D-19	Varied
Toluene Diisocyanate (TDI), 80:20	
Index	114
Parts	59.7
Bench Foaming Conditions	
Polyol Charge, g	600
Mixing Speed, rpm	2700
Box Size, in	14 x 14
Oven Curing Temperature, °C (°F)	125 (257)
Oven Curing Time, min	10

**Table 2: Properties of Foam with Niax Catalyst A-33**

	Niax Catalyst A-33					Niax Catalyst A-10/A-33 <sup>(1)</sup>				
Amine Level	0.26	0.26	0.26	0.21	0.31	0.25	0.25	0.25	0.20	0.30
D-19 Level	0.22	0.25	0.28	0.25	0.25	0.22	0.25	0.28	0.25	0.25
Polyol Temperature, °F (°C)	74 (23.3)					74 (23.3)				
Cream Time, sec	14	13	12	14	12	13	13	12	13	12
Rise Time, sec	101	96	93	102	92	102	97	93	102	92
Top Collapse, in	0.4	0.4	0.4	0.3	0.2	0.4	0.3	0.3	0.3	0.2
Height of Rise, in	13.0	13.0	13.2	13.0	13.1	13.0	13.0	13.4	13.1	13.2
Cells per in	45–50					45–50				
Breathability, SCFM										
Top	5.5	5.2	4.7	5.2	4.7	5.5	5.2	4.7	4.7	5.2
Middle	3.0	2.3	1.6	2.3	2.3	2.9	2.5	1.8	2.0	2.3
Bottom	0.9	0.7	0.6	0.7	0.7	0.8	0.7	0.6	0.7	0.7
Density, pcf										
Top	1.13	1.10	1.12	1.11	1.12	1.13	1.09	1.09	1.10	1.10
Middle	1.13	1.12	1.13	1.11	1.13	1.12	1.10	1.11	1.11	1.11
Bottom	1.25	1.24	1.23	1.23	1.24	1.23	1.20	1.21	1.21	1.21
IFD, 12 in x 12 in x 4 in, lb										
25%	30	28	31.5	29	28	28	31	32	32	30
65%	53	51	55	50	50	55	53	57	57	54

(1) 3/1 Blend

**Patent Status**

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or

recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

## Product Safety, Handling and Storage

Customers should review the latest Material Safety Data Sheet (MSDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, and any special storage conditions required for safety. MSDS are available at [www.momentive.com](http://www.momentive.com) or, upon request, from any Momentive Performance Materials (MPM) representative. **For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center.** Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

## Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

From automotive to healthcare, from electronics to construction, products from Momentive Performance Materials Inc. are practically everywhere you look. We are a global leader in silicones and advanced materials with a 70+ year heritage of innovation and being first to market – with performance applications that improve everyday life. By knowing our customers' needs and creating custom technology platforms for them, we provide science based solutions to help customers increase performance, solve product development issues and engineer better manufacturing processes.

## Contact Information

For product prices, availability, or order placement, contact our customer service by visiting [www.momentive.com/Contacts](http://www.momentive.com/Contacts)

For literature and technical assistance, visit our website at: [www.momentive.com](http://www.momentive.com)

**Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.**

**\*Niax is a trademark of Momentive Performance Materials Inc.**

## DISCLAIMER

The information provided herein was believed by Momentive Performance Materials Inc. (collectively with its subsidiaries, "Momentive") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for user's intended application or use. All products supplied by Momentive are subject to Momentive's standard terms and conditions of sale. **MOMENTIVE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY MOMENTIVE**, except that the product shall conform to Momentive's specifications. Nothing contained herein constitutes an offer for the sale of any products.